LINQCELL **VRB-MEM Series**

Ion Exchange Membranes for Redox Flow Batteries

- Available in different thicknesses
- High acid capacity, high conductivity, and extended service life
- Designed as ion exchange membranes for redox flow batteries

LINQCELL VRB-MEM Membranes are perfluorinated cation exchange polymers in the acid H^+ form produced through solution casting. This chemistry and manufacturing method provide several benefits, including high acid capacity and conductivity, enhanced crystallinity and tensile strength, reduced linear expansion and anisotropy, and an extended service life. These characteristics make **LINQCELL VRB-MEM Membranes** highly recommended for use as ion exchange membranes in redox flow batteries, particularly in all-vanadium flow batteries.

LINQCELL VRB-MEM Membranes are available in two standard thicknesses—50 µm (VRB-MEM50) and 75 µm (VRB-MEM75)—and can also be custom-fabricated to meet specific requirements. The maximum roll width is 75 cm.

Specifications

Property	Unit	VRB-MEM50	VRB-MEM75
Physical Properties			
Thickness	µm	50 (±2)	75 (±2)
Specific gravity	–	2	
Tensile strength (MD/TD)	MPa	38/38	
Modulus	MPa	600	
Elongation to break	%	160	
Hydrolytic Properties			
Water content[1]	%water	5	
Water uptake[2]	%water	49	
Linear expansion from 23 °C, 50% RH to water soaked, 23 °C to water soaked, 100 °C	%	 3 5	
Other Properties			
Available acid capacity	$meq \cdot g^{-1}$	1	
Conductivity	$S \cdot cm^{-1}$	0.1	
Hydrogen permeability	$mL/(min \cdot cm)$	0.008	–

[1] *Water content of the membrane conditioned at 23 °C and 50% relative humidity, based on dry weight.*
[2] *Water absorption from a dry membrane to a conditioned state in water at 100 °C for 1 hour, based on dry weight.*

Storage and Handling

Keep unopened rolls of LINQCELL membranes in their original packaging, away from sunlight, at 10–30 °C and 30–70% humidity. Let the roll adjust to the processing area temperature for 24 hours before opening. Once exposed, the membrane will adapt to the surrounding humidity, which may affect its dimensions.

Europe
Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada
80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com

North America
36927 Schoolcraft Rd
Livonia, MI 48150
United States
Phone: +1 (313) 558-8243
Email: info@caplinq.com

South East Asia
S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60 (12)4302223
Email: info@caplinq.com