


CHEMLINQ™ RCS 560

Rubber Cleaning Sheets



- High torque, high cleaning efficiency for deep residues
- No mold abrasion and corrosion
- Little smell and fume

CHEMLINQ™ RCS 560 rubber cleaning sheets are formulated to effectively remove EMC-related contaminants from mold surfaces. Specifically designed for the semiconductor industry, these sheets are ideal for cleaning molds used in the production of ICs, diodes, transistors, and LEDs.

During the molding and curing process, **CHEMLINQ™ RCS 560** applies high pressure and conforms well to the mold surface. It exhibits stronger mechanical strength leading to more aggressive cleaning targeting deep-seated residues and stains in air vents, corners, gate areas, and other intricate mold features. **CHEMLINQ™ RCS 560** also fills complex shapes and micro-sized mold cavities without incomplete fill issues. It does not require lead frames nor preheating during mold cleaning, further streamlining the cleaning process.

Specifications

Property	Value	Unit
Appearance	Solid, white strips	–
Specific Gravity	1.12 – 1.22	–
Minimum Torque	1.12 ±0.12	N.m
Maximum Torque	10.1±0.5	N.m
Solubility	Insoluble in water	–
Dimension	Customizable	–

Recommend Processing Parameters

Parameter	Value	Unit
Curing Temperature	160 – 190	°C
Curing Temperature	300 – 500	s
Mold Clamp Pressure	30 – 150	ton

Instructions for Use

1. Place the strips on the mold following the standard operating procedure. Strip quantity depends on the mold dimension. If the rubber flow does not cover all cavities, add more rubber strips.
2. Clamp the mold and compress to fill all the cavities. Adjust the cure time based on the mold machine settings.

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



North America

36927 Schoolcraft Rd
Livonia, MI 48150
United States
Phone: +1 (313) 558-8243
Email: info@caplinq.com

South East Asia

S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60 (12)4302223
Email: info@caplinq.com

Cure time depends on the mold temperature. Higher mold temperatures generally require a shorter cure time, and vice versa.

- Cure time at 165 °C = approx. 420 s
 - Cure time at 175 °C = approx. 300 s
3. After cleaning, unload the rubber sheets and inspect them for any remaining impurities. Assess the condition of the mold press to ensure it is in proper working order.
 4. Repeat the process until the desired cleaning result is achieved. Typically, 3 to 6 shots are required, depending on the mold conditions.

Caution for Use

Use the product in a well-ventilated area. Avoid touching hot cured rubber with your skin. Always follow safety guidelines and wear protective equipment when handling. For more safety information, check the Material Safety Data Sheet (MSDS).

Storage and Handling

CHEMLINQ™ RCS 560 is packaged in PE bags. Store the product in a cool (temperature < 30 °C), dark place, away from direct sunlight. The shelf life is 6 months when stored at 30 °C and 12 months below 25°C. Keep the container sealed to prevent moisture contamination when not in use. Reseal the bag immediately after each use.

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



North America

36927 Schoolcraft Rd
Livonia, MI 48150
United States
+1 (313) 558-8243
Email: info@caplinq.com

South East Asia

S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60 (12) 4302223
Email: info@caplinq.com