

ALPHA® EF-8800HF

Halogen-Free, High Reliability, Alcohol Based No-Clean Wave Soldering Flux for Thick Board Applications



DESCRIPTION

ALPHA EF-8800HF is an alcohol based flux designed for both standard and thicker, high-density PCBs in Lead-free process. This flux shows stable performance even under long exposure to higher preheat and higher solder pot temperature. **ALPHA EF-8800HF** is formulated to have low bridging on bottom side QFPs, as well as provide superior performance in pin testing, hole-fill and solderballing. Additionally, it provides good Lead-free solder joint cosmetics with an evenly spread, tack free residue.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

Features for Lead-free

- Robust soldering performance even under high top-side preheat >125 °C, Pb-free pot temperatures exceeding 270 °C, contact times > 7 seconds
- Excellent hole fill demonstrated by >92% yield on 15 mil holes
- Low bridging performance on connectors, 0.65 mm and 0.80 mm QFPs
- Pin testable

Benefits

- Evenly spread, tack free residue.
- Excellent Lead-free soldering performance on various board finishes.
- Can be used in Lead-free process
- Halide free
- Compliant to all current halogen-free industry standards

APPLICATION GUIDELINES

PREPARATION: In order to maintain consistent soldering performance and electrical reliability, it is important to begin the process with circuit boards and components that meet established requirements for solderability and ionic cleanliness. It is suggested that assemblers establish specifications on these items with their suppliers and that suppliers provide Certificates of Analysis with shipments and/or assemblers perform incoming inspection. A common specification for the ionic cleanliness of incoming boards and components is 5µg/in² maximum, as measured by an Omegameter with heated solution.

Care should be taken in handling the circuit boards throughout the process. Boards should always be held at the edges. The use of clean, lint-free gloves is also recommended. Conveyors, fingers and pallets should be cleaned. ALPHA brand AutoClean 40 cleaner is recommended for this process.

FLUX APPLICATION: ALPHA EF-8800HF can be applied by spraying. When spray fluxing, the uniformity of the coating can be visually checked by running a piece of cardboard over the spray fluxer or by processing a board-sized piece of tempered glass through the spray and then through the preheat section.

Operating Parameter	
Amount of Flux	(150 to 465) µg/cm ² or (1000 to 3000) µg/in ² of solids
Topside Preheat Temperature	90 to 135 °C (194 to 275 °F)
Bottom side Preheat Temperature	0+32 °C (0+89.6 °F) vs. Top-Side
Conveyor Angle	5 to 8°
Conveyor Speed	0.3 to 1.5 m/min (0.98 to 4.92 ft/min.)
Contact Time in the Solder (includes Chip Wave and Primary Wave)	3 to 10 seconds
Solder Pot Temperature	250 to 270 °C (482 to 518 °F)
These are general guidelines, which have proven to yield excellent results; however, depending upon your equipment, components, and circuit boards, your optimal settings may be different. In order to optimize your process, it is recommended to perform a designed experiment, optimizing the most important variables (amount of flux applied, conveyor speed, topside preheat temperature, solder pot temperature and board orientation).	

CONTROL:

ALPHA EF-8800HF flux should be applied by spray fluxing application. A uniform coating of flux is essential to successful soldering. When applying flux, it is important to run a series of tests to ensure that the flux is being applied uniformly, that it is penetrating from top to bottom of the board on all holes to be soldered and to make sure that excessive amounts of flux are not being applied. There are various methods for conducting these tests. Consult with your local ALPHA Customer Technical Service Representative for more information.

RESIDUE REMOVAL: ALPHA EF-8800HF is a no-clean flux and the residues are designed to be left on the board. If desired, flux residues can be removed with ALPHA SM110E solvent cleaner or ALPHA 2110 saponifier cleaner and with other commercially available solvent cleaners and saponifier cleaners.

HALOGEN CLASS

Standard	Requirement	Test Method	Status
IEC 61249-2-21	Post soldering residues contain <900ppm each or total of <1500ppm Br or Cl from flame retardant source	TM EN 14582 Solids extraction per IPC TM 2.3.34	PASS
JEDEC A Guideline for Defining "Low Halogen" Electronic products	Post soldering residues contain <1000ppm Br or Cl from flame retardant source		PASS

TECHNICAL DATA

Item	Specification	Item	Specification
Appearance	Clear, Pale Yellow Liquid	pH, 5% v/v aqueous solution	3.1
Solids Content, wt/wt	6.0%	Recommended Thinner	ALPHA 425
Specific Gravity @ 25 °C (77 °C)	0.799 ± 0.003	Shelf Life	12 months
Acid Number (mg KOH/g)	34.0 ± 5.0	IPC J-STD-004B Designation	ORL0
Flash Point (T.C.C.)	17 °C		

CORROSION & ELECTRICAL TESTING – SAC305 ALLOY
CORROSION TESTING

Test	Requirement for ORL0	Results
Copper Mirror Tests IPC-TM-650 Test Method 2.6.32	No complete removal of copper	PASS
Copper Corrosion Test IPC-TM 650 Test Method 2.3.15 JIS 3197 Test Method 8.4.1	No evidence of corrosion	No Evidence of Corrosion

IPC J-STD-004A SURFACE INSULATION RESISTANCE

Test	Conditions	Requirements	Results
"Comb-Down" Un-cleaned	85 °C/85% RH, 7 days	$> 1.0 \times 10^8 \Omega$	$7.0 \times 10^8 \Omega$
"Comb-Up" Un-cleaned	85 °C/85% RH, 7 days	$> 1.0 \times 10^8 \Omega$	$2.2 \times 10^{10} \Omega$
Control Boards	85 °C/85% RH, 7 days	$> 1.0 \times 10^9 \Omega$	$5.0 \times 10^{10} \Omega$
IPC Test Condition (per J-STD-004A): -50V, measurement @ 100V/IPC B-24 board (0.4 mm lines, 0.5 mm spacing).			

IPC J-STD-004B SURFACE INSULATION RESISTANCE

Test	Requirements ($< 1.0 \times 10^8$ allowed during initial 24 hrs.)	Results (<i>min. of all measurements recorded</i>)		
		< 24 Hrs	24 to 168 Hrs	Visual
"Comb-Down" Un-cleaned	$1.0 \times 10^8 \Omega$ minimum	$3.9 \times 10^9 \Omega$	$1.1 \times 10^{10} \Omega$	PASS
"Comb-Up" Un-cleaned	$1.0 \times 10^8 \Omega$ minimum	$8.4 \times 10^9 \Omega$	$4.5 \times 10^{10} \Omega$	PASS
Control Boards	$1.0 \times 10^9 \Omega$ minimum	$2.1 \times 10^{10} \Omega$	$1.2 \times 10^{11} \Omega$	NA
IPC Test Condition (per J-STD-004B TM2.6.3.7): IPC B-24 coupons, 12V, 40 °C, 90% RH, measurements recorded @ 20min intervals				

BELLCORE ELECTROCHEMICAL MIGRATION RESISTANCE

Test	SIR (Initial)	SIR (Final)	Requirement	Result	Visual Result
"Comb-Up" Un-cleaned	$1.9 \times 10^{11} \Omega$	$1.3 \times 10^{11} \Omega$	$SIR (Initial)/SIR (Final) < 10$	PASS	PASS
"Comb-Down" Un-cleaned	$6.0 \times 10^{10} \Omega$	$3.9 \times 10^{11} \Omega$	$SIR (Initial)/SIR (Final) < 10$	PASS	PASS
Control	$2.6 \times 10^{11} \Omega$	$5.0 \times 10^{11} \Omega$	Not applicable	N/A	N/A
Bellcore Test Condition (per TR-NWT-000078, Issue 3): 85 °C/85%RH/500 Hours/10V, measurement @ 100V/IPC B-25 B Pattern (12.5 mil lines, 12.5 mil spacing)					

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. **READ IT THOROUGHLY PRIOR TO PRODUCT USE.** Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. **NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE.** The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.